# $\underset{\text{polyester film}}{\text{Mylar}}$

### Type EL-21 750–1400 Gauge

#### **Product Description**

Mylar<sup>®</sup> polyester films are flexible, strong, and durable films with an unusual balance of properties, making them suitable for a variety of industrial applications. The excellent dielectric strength, moisture resistance, and physical toughness make Mylar<sup>®</sup> a very versatile and functional insulating material.

#### **Typical Properties**

Mylar<sup>®</sup> films offer high dielectric strength, good chemical resistance, and exceptional durability in high-temperature environments.

#### **Applications**

Type EL-21 films, similar to Type MO films, are heavy gauge insulating films designed for generalpurpose electrical/electronic applications, such as transformers, laminates, bus bars, and punched parts.

Tensile Strength MD/TD,* kg/mm² (kpsi)	Elongation MD/TD,* %	Dimensional Stability MD/TD,* % Shrinkage	Opacity, %	Density, g/cm³	Dielectric Strength (AC), kV (Min.)		
19/21 (27/30)	140/115	1.6/0.9	38	1.3928	17.5		
19/20 (27/29)	150/130	1.6/1.1	41	1.3920	18.4		
19/20 (27/29)	150/140	1.5/1.1	42	1.3925	19.0		
18/17 (26/25)	170/170	1.3/0.8	46	1.3925	20.0		
-	Tensile Strength MD/TD,* kg/mm <sup>2</sup> (kpsi) 19/21 (27/30) 19/20 (27/29) 19/20 (27/29)	Tensile Elongation   Strength MD/TD,*   MD/TD,127/30) 140/115   19/21 (27/30) 140/115   19/20 (27/29) 150/130   19/20 (27/29) 150/140	Tensile Dimensional   Strength Elongation MD/TD,*   MD/TD,* Elongation MD/TD,*   19/21 (27/30) 140/115 1.6/0.9   19/20 (27/29) 150/130 1.6/1.1   19/20 (27/29) 150/140 1.5/1.1	Tensile Strength MD/TD,* Dimensional Stability MD/TD,* Opacity, %   19/21 (27/30) 140/115 1.6/0.9 38   19/20 (27/29) 150/130 1.6/1.1 41   19/20 (27/29) 150/140 1.5/1.1 42	Tensile Strength MD/TD,* Dimensional Stability MD/TD,* Density,   19/21 (27/30) 140/115 1.6/0.9 38 1.3928   19/20 (27/29) 150/130 1.6/1.1 41 1.3920   19/20 (27/29) 150/140 1.5/1.1 42 1.3925		

#### **Typical Values for Major Properties**

\*MD = Machine Direction, TD = Transverse Direction

# Ordering Information *Slit Rolls*

#### Standard Roll Size

ID, cm (in)	OD, cm (in)		
7.6 (3)	33 (13)		
7.6 (3)	41 (16)		
7.6 (3)	46 (18)		

## Approximate Length for 7.6 cm (3 in) ID $\times$ 33 cm (13 in) OD Roll

		••			
Nominal Thickness,	Nominal Length,	Nominal Thickness,	Nominal Length,		
μm (Gauge)	m (ft)	μm (Gauge)	m (ft)		
188 (750)	415 (1,360)	188 (750)	1,650 (5,400)		
225 (900)	350 (1,140)	225 (900)	1,380 (4,520)		
250 (1,000)	310 (1,020)	250 (1,000)	1,240 (4,070)		
350 (1,400)	220 (730)	350 (1,400)	870 (2,850)		

#### **Master Rolls**

Master rolls are much longer lengths, splice-free, and available on 25.4 cm (10 in) ID cores. Master rolls are available in selected widths in minimum order quantities of 15,900 kg (35,000 lb) per order, with a minimum of 4,540 kg (10,000 lb) per item.

**Approximate Length for Master Rolls** 

DuPont Teijin Films Barley Mill Plaza Wilmington, DE 19880-0027 Product Information: (800) 635-4639 Fax: (302) 992-5453

These values are typical performance data for Mylar<sup>®</sup> polyester film; they are not intended to be used as design data. We believe this information is the best currently available on the subject. It is offered as a possible helpful suggestion in experimentation you may care to undertake along these lines. It is subject to revision as additional knowledge and experience is gained. DuPont Teijin Films makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. This publication is not a license to operate under, or intended to suggest infringement of, anyexisting existing patents.

**CAUTION:** Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102.

Mylar<sup>®</sup> Only by DuPont Teijin Films