

Grades FHT & SG -200

Grade FHT – Flexible, High-Temperature Laminate

- Highly Flexible
- Excellent Dielectric Strength
- High Heat Resistance
- Ideal For Dry-Type Transformers
- Easily Fabricated
- Asbestos-Free

Glastic® Grade FHT (Flexible High Temperature) Laminate provides numerous high-performance features and benefits, such as high flexibility and excellent dielectric strength at elevated temperatures. It also exhibits the highest UL temperature index in the industry for a flexible glass-reinforced polyester in 1/32 inch and 1/16 inch thicknesses:

- | | |
|---------------------------------|---------------------------------|
| • 1/32 inch – 190° C Electrical | • 1/16 inch – 200° C Electrical |
| • 1/32 inch – 190° C Mechanical | • 1/16 inch – 200° C Mechanical |

With its high resistance to heat, Glastic's FHT Laminate offers a cost-effective alternative to aramid paper in 220° C insulation systems. Typical applications include layer and core insulation for dry-type transformers.

Glastic Grade FHT Laminate standard color is tan.

Grade SG-200 – High-Strength & High-Temperature Laminate

- Extremely Strong
- Excellent Retention Of Properties At Elevated Temperatures
- Ideal For High Temperature Applications
- Easily Fabricated
- Asbestos-Free

Glastic Grade SG-200 High-Strength & High-Temperature Laminate offers the same high-performance features and benefits as Glastic's FHT Laminate. In addition, SG-200 offers much higher mechanical strengths than FHT with temperature ratings of up to 210° C.

Because of its capabilities, Glastic SG-200 is ideal for a wide variety of product applications requiring high-temperature NEMA GPO-1 products. Grade SG-200 is also a superior replacement material for epoxy-bonded mica in layer insulation applications. SG-200 has a UL Temperature Index of 210° C Electrical and 210° C Mechanical.

Glastic Grade SG-200 is available in thicknesses of 1/32" to 1-1/4" and in a natural tan color. Special sheet sizes of 64" x 64" are available for large lifting magnets.



Ventilated Dry-Type Transformer Coil. Both Glastic SG-200 and FHT Laminates are used in a wide variety of dry-type transformer applications.

Grades FHT & SG -200

GLASTIC LAMINATES PROPERTY TABLE

TYPICAL AVERAGE VALUES¹

GENERAL INFORMATION	UNIT	ASTM/UL NUMBER	GLASTIC GRADE SG-200	GLASTIC GRADE FHT
Part Number			1906	1800
Color, Standard			Natural/Tan	Natural/Cream
MECHANICAL PROPERTIES				
NEMA Grade	----	----	GPO-1	----
Tensile Strength	Psi	D638	12,500	10,500
Tensile Modulus	Psi x 10 ⁶	D638	1.7	----
Flexural Strength	Psi	D790	29,000	----
Compressive Strength	Psi	D695	36,000	14,000
Shear Strength	Psi	D732	11,100	----
IZOD Impact Strength (notched)	ft.lb./in.	D256	12.0	10.0
Water Absorption	% by wt.	D570	0.3	1.1
Specific Gravity	----	D792	1.70	1.60
ELECTRICAL PROPERTIES				
Electrical Strength - Perpendicular S/T in air	Vpm	D149	500	450
Electrical Strength - Perpendicular S/T in oil	Vpm	D149	625	570
Electrical Strength - Parallel S/S in oil	kV	D149	50	60
Arc Resistance	Sec.	D495	120/180 ²	139
IEC Track Resistance (CTI)	V.	UL746A	500+	500+
UL High Voltage Track Rate	In./Min.	UL746A	0	0
Permittivity, 60 Hz	----	D150	4.6	6.4
Dissipation Factor, 60 Hz	----	D150	0.037	0.070
Permittivity, MHz	----	D150	3.7	4.2
Dissipation Factor, MHz	----	D150	0.013	0.033
Insulation Resistance	Ohm x 10 ¹²	D257	145.0	----
FLAME-RESISTANCE PROPERTIES				
UL Subject 94	----	UL94	HB	HB
UL Hot Wire Ignition	Sec.	UL746A	0.028 in./35 0.058 in./39	0.028 in./49 0.058 in./102
UL High Amp Ignition	#Exposure	UL746A	200+	200+
Oxygen Index	%O ₂	D2863	21.8	21.8
THERMAL PROPERTIES				
Coefficient of Thermal Expansion	In/In/° C x 10 ⁻⁵	D696	2.0	----
Thermal Conductivity	BTU/Hr/Ft ² /In/° F	C177	1.7	----
UL Temperature Index - Electrical	° C	UL 746B	210	0.028 in./190 0.058 in./200
- Mechanical	° C	UL 746B	210	0.028 in./190 0.058 in./200
UL Recognition File Number	----	----	E81928	E81928

¹ Typical average values for testing 0.063 inch thick material. Values will vary somewhat from thickness to thickness within a material grade.

² Post-cured



GLASTIC CORPORATION

4321 Glenridge Road | Cleveland, OH 44121-2891 | phone 216-486-0100 | fax 216-486-1091 | www.glastic.com

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Glastic products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. **THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** Under no circumstances shall we be liable for incidental or consequential loss or damage.

Glastic® is a registered trademark of Glastic Corporation. UL® is a registered trademark of Underwriters Laboratories, Inc. ©2002 Glastic Corporation. All Rights Reserved. Printed in USA GL-1070B0 0602