

Glastic Composite Tubing

Pultruded Round & Square Tubing

- UL Recognized
- Highly Flame-Resistant
- Arc-and Track-Resistant
- Uncommon Dimensional Stability
- Strong & Durable, yet Easily Cut and Chamfered
- Cost-Effective

Glastic® Grade UTR Pultruded Tubing is a fiberglass-reinforced thermoset polyester tube. It meets the requirements of NEMA grade GPO-3, as well as being recognized by Underwriters Laboratories®.

Highly flame-, arc-, and track-resistant, Glastic UTR pultruded tubing provides reliability in a wide range of applications. The product exhibits exceptional dimensional stability and is impervious to high humidity or immersion. Also, because it is constructed of a reinforced plastic composite, it is electrically non-conductive.

This tubing has a UL index rating of 130° C electrical and 160° C mechanical. Its burst strength is 1,200 to 1,400 psi, yet it is easily chamfered and cut with carbide or diamond saws.



Stock Sizes

Glastic pultruded tubing is available in a variety of stocked sizes. (See table on back for more detailed information).

Custom Performance/ Standard Sizes

By changing the raw materials, stock sizes can be modified to meet your specific performance requirements. No new tooling is required.

Custom Tubing Available

Custom tubing can also be produced to meet your specific requirements such as:

- High tensile strength
- High flexural strength
- Increased stiffness
- UV stability
- Custom colors (ask about Alpha color options)
- Corrosion and chemical resistance
- Custom shapes



www.glastic.com

Glastic Composite Tubing

Pultruded Tubing Sizes & Properties

STOCK SIZES IN INCHES			
TUBE SIZE	PART NUMBER	NOMINAL OD	NOMINAL ID
1/2	F800608	.513	.406
1/2	F810608	.500	.375
11/16	CUSTOM	.680	.520
3/4	F851012	.75	.625
3/4	F811012	.733	.632
7/8	CUSTOM	.875	.715
1	F801316	.995	.816
1	F811316	.990	.824
1-1/16	F801417	1.070	.890
1-1/4	F801720	1.250	1.071
1-1/4	F811620	1.240	1.012
1-1/2	F802024	1.494	1.250
1-1/2	F812024	1.494	1.262
1-9/16	F802125	1.570	1.330
1-3/4	F802428	1.742	1.500
1-3/4	F812428	1.742	1.512
1-3/4	CUSTOM	1.742	1.250
2	F802832	1.994	1.750
2	F812832	1.986	1.762
2	F842832	1.994	1.744
2-5/16	F803137	2.286	1.926
2-1/2	F803440	2.492	2.125
2-1/2	F813440	2.483	2.146
2-1/2	F830190	2.492	2.116
2-13/16	F803945	2.786	2.411
3	F804248	2.992	2.617

RECTANGULAR AND SQUARE TUBING				
TUBE SIZE	PART NUMBER	NOMINAL OD	NOMINAL ID	WALL THICKNESS
1-1/2	F822024	1.500	1.250	.125
2	F822432	2.000	1.500	.250
1-1/16 X 13/16	CUSTOM	1.090 X .790	.925 X .625	.083
1-3/16 X 13/16	CUSTOM	1.195 X .793	1.015 X .610	.092

GENERAL INFORMATION	TEST PROCEDURE	UNITS	TYPICAL VALUE
MECHANICAL PROPERTIES			
*Tensile Strength	D638-97	Psi x 10E3	30.7
*Tensile Modulus	D638-97	Psi x 10E6	2.28
*Flexural Strength (Tube)	D790-97A	lbs.	134
*Flexural Modulus (Tube)	D790-97A	lbs/in	4180
*Compressive Strength (Tube)	D2412-96A	lbs.	126
*Compressive Modulus (Tube)	D2412-96A	lbs/in/in	3930
Burst Strength	D1180-57	Psi	1300
Water Absorption	D570	% by wgt.	0.5
ELECTRICAL PROPERTIES			
Arc Resistance	ASTM D495	Sec.	150
Inclined Plane Track Resistance	ASTN D2303	Min.	300
FLAME-THERMAL PROPERTIES			
Flame Resistance	NEMA L1-1		Class 0
UL Temperature Index	UL 746B		
Electrical		°C	130
Mechanical		°C	160
* Based on .75" OD tube, .050" wall thickness			

TOLERANCES – ASTM (ABBREVIATED)	
OD/ID	WALL THICKNESS
± .010", UNDER 2" DIAMETER	± .010", UNDER .067" WALL
± .020", 2" DIAMETER & OVER	± 15%, FOR .067" WALL & OVER



GLASTIC CORPORATION

4321 Glenridge Road | Cleveland, OH 44121-2891 | phone 216-486-0100 | fax 216-486-1091 | www.glastic.com

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Glastic products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. **THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** Under no circumstances shall we be liable for incidental or consequential loss or damage.

Glastic® is a registered trademark of Glastic Corporation. UL® is a registered trademark of Underwriters Laboratories, Inc. ©2002 Glastic Corporation. All Rights Reserved. Printed in USA GL-1106 0602